

**POLYPROPYLENE**

**18C3A**

**DESCRIPTION:** Impact Copolymer

**FEATURES:** Excellent Impact strength and long term heat aging. Product does not contain animal derived components.

**APPLICATIONS:** Injection molding: electrical housings

PROPERTY	NOMINAL VALUE	SI UNIT	NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	3.0	g/10 min.			D 1238
Density	0.90	g/cm <sup>3</sup>			D 1505
Tensile					
Yield Strength	24	MPa	3500	psi	D 638
Ultimate Elongation	550	%	550	%	
Modulus	1138	MPa	165	kpsi	
Flexural Modulus	1069	MPa	155	kpsi	D 790
Deflection Temperature @ 66 psi	85	°C	185	°F	D 648
Rockwell Hardness			75	R	D 785
Notched Izod @ 23°C	NB*	J/m	NB*	ft-lb/in	D 256
Gardner Impact @ -18°C	>36	J	>300	in-lb	D 5420

Sept-08

**Regulatory**

FDA - 21 CFR 177.1520 (c) 3.1a

UL listed 105 °C LTHA

---

118 Huntsman Way, Longview, TX 75602 · Tel: 1-800-985-7303

The data and information represented herein refer to typical values obtained in our laboratories by the methods or apparatuses indicated, and should be so considered. Since processing variables are a major factor in product performance, this information should serve only as a guide. Since customers' testing conditions are outside our control, the reproducibility of our data in a customer's testing facility is not guaranteed. Customer should confirm results under its testing conditions. There is no implied warranty of merchantability or fitness for a particular purpose. Establishing satisfactory performance of the product for the intended application is the customer's sole responsibility. No warranty is given concerning the existence or non-existence of any patents claiming any pertinent subject matter presented herein. The Company assumes no obligation, express or implied, or liability for use of or reliance on the information and data presented. FHR disclaims all product warranties expressed or implied, including warranties of fitness for particular purpose or of merchantability. Further, this product is not intended for use in the manufacture of any form of implanted medical or surgical device.