



Polypropylene Automotive Grades

Grade	Type	Melt Flow (g/10 min)	Izod @ 23C (ft-lb/in)	Flex Modulus Tangent (Kpsi)	Processing/Product Types	Ford	Chrysler
AP6106-HS	Impact Copolymer	6	2.3	180	Interior Trip, Consoles, Pillars		DB500 CPN5071
AP6112-HS	Impact Copolymer	12	2.3	170	Injection molding, automotive interior trim		
AP6412-HS	Impact Copolymer	12	2.4	165	Injection molding, automotive interior trim		
AP5325-HS	Impact Copolymer	20	2.2	200	Steering Wheel Shrouds, Door Panels, Trims and Consoles	WSS-M4D638-B	DB500 CPN 3560 DB500 CPN 3562
AP6120-HS	Impact Copolymer	20	2.2	168	Injection molding, large interior parts and trims		